

		_	
W	וים	D	,
V	Ľ	I١	

Zinc Manganese Dioxide Battery

DATE:

1.5V

Zinc Manganese Coin type Battery **Specification**

10mAh

Model: <u>LR63</u>

Prepared By/Date	Checked By/Date	Approved By/Date

Important Notice

These data sheets contain information specific to batteries manufactured at the time of its publication.

Content herein do not constitute a warranty.

Copyright @ Xtra-Power Battery .All rights reserved



VER:

Zinc Manganese Dioxide Battery

DATE:

PRODUCT SPECIFICATION

1. Applicability: This specification is applicable to **LR63** coin type zinc manganese dioxide battery.

SPECIFICATION

1. Cross Reference:

				U.S.A		
	IEC	JAPAN	Ray-O-Vac	SWITZERLAND	GERMANY	PRODUCTS
	LR63		RW327	379	V379	AG0

2. Chemical System : Zinc-Manganese Dioxide (Potassium Hydroxide Electrolyte)

3. Nominal Voltage: 1.50V

10mAh (continuously discharge at 20±2 $^{\circ}\mathbb{C}$ under 6.8k $^{\Omega}$ load

4. Standard Capacity: to 0.9V end-point voltage)

5. Approximate Weight: 0.28g

6. Dimensions & Structure : Dimensions & structure of the cell are shown in the attached Fig. 1.

7. Terminal Materials: Negative: Ni plated/Fe/Cu plated or gold plated steel

Positive: Ni plated steel



VER:

Zinc Manganese Dioxide Battery

DATE:

8. Characteristics :

Characteristics of the cell are shown in the following table.

Storage	Characteristics	Conditions	
Characteristi	cs		
Initial	1.510V or higher	DC Voltmeter: The tolerance is ±0.005V and the	
After 12 months	1.500V or higher	input resistance is 1M Ω or more.	
Initial	1.520V or higher	DC Voltmeter : Same as above.	
After 12 months	1.490V or higher	Load Resistance : 22k Ω , 0.8Sec.	
Output			
Initial	150hrs or longer	Discharge Resistance : 22k Ω End-Point Voltage : 0.9V	
After 12 months	135hrs or longer		
yte Leakage P	roof Characteristic	es	
There are no bulging or deformation of cells in excess on of maximum dimensions shown in attached Fig. 1 by 0.2mm or more. There are no visible electrolyte leakage.		Humidity: (65±20)%RH Load Resistance: 22kΩ Overdischarge Time: 48hrs (discharge after having	
	Initial After 12 months Initial After 12 months Output Initial After 12 months Output There are deformation of maximus shown in atta by 0.2mm of	Characteristics Initial After 12	




VER:

DATE:

Zinc Manganese Dioxide Battery

9. Discharge Curve:

Load Resistance : $22k \Omega$ End-Point Voltage: 0.9V



10. Markings on Product:

- (1) Battery Type: L521
- (2) Brand:
- (3) Polarity: "+" at the bottom ("--" not indicated)
- (4) Other specified markings

11. Caution for Use:

- (1) Since the button cell is not manufactured for recharging, there are risks of electrolyte leakage or causing damage to the device if the cell is charged.
- (2) The button cell shall be installed with its "+" and "--" sign according to the instruction shown on the applied device.
- (3) Short-circuiting, heating, disposing of in fire, or dissembling the button cell shall be prohibited.

12. Warranty:

12 months shelf life after delivery.

